

# Easy Mask

masking film - roll

## **CHARACTERISTICS**

Masking film for quickly covering car body components. The masking film provides no paint adhesion.

## **PRODUCT DATA**

Raw material: HDPE Density: 0,95 g/cm<sup>3</sup> Thickness: 9 µm

Tensile Strength machine direction - ASTM D 882: 70 N / mm $^2$  Tensile Strength transverse direction - ASTM D 882: 28 N / mm $^2$  Elongation at break machine direction - ASTM D 882: 422 % Elongatin at break transverse direction - ASTM D 882: 893 %

Dart drop - ASTN 1709-91: 3,45 g / μm

This technical information has been given to the best of our knowledge. The above mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.

### **HANDLING**

Indications for storage and application

Storage time: 12 months from delivery date Storage temperature: + 20° C /± 10° C

Relative humidity (RH): 30 - 90 %

Storage: in closed rooms

exposure to UV-radiation: to avoid



### **SAFETY ISSUES**

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE

Telefon Telefax E-Mail +49 (0) 4122/717 -0 +49 (0) 4122/717-158 info@vosschemie.de www.carsystem.org www.vosschemie.de